

Product:	Roxul[®] Stonewool	P.D.S 12
Type:	LIGHT-WEIGHT SEMI-RIGID SLAB	
Name:	RockTech S 200 (for use up to 350°C)	Page 1 of 4

Description

Roxul Stonewool RockTech S 200 is a high quality resin-bonded light-weight semi-rigid mineral wool slab with excellent thermal, acoustic and fire safety properties.

Applications for RockTech S 200 can be used for low temperature thermal insulation and for general acoustic applications.

Standard Sizes (mm)

Thickness	Dimensions	Slab Per Pack
25	1200 x 600	12
38	1200 x 600	8
50	1200 x 600	6
75	1200 x 600	4
100*	1200 x 600	3

* not a stock item

Special sizes and facings are available to order but may be subject to minimum production quantity requirements.

Product Performance and Properties

Density: > 60 kg/m³ (nominal):- being delivered density according to ASTM C612.- 93

Service Temperature: Maximum continuous service temperature on plain surface 350°C (662°F) according to ASTM C411.

Thermal Conductivity (typical data): Tested in accordance with DIN 52612.

Mean Temp °C	50	100	150	200	250	300
K value W/m °C	0.039	0.048	0.058	0.071	0.087	0.107

PRODUCT DATA SHEET

REVISION:	3
DATE OF ISSUE:	Nov 02
CHKD:	BH APPV: IRS

Product:	Roxul[®] Stonewool	P.D.S 12
Type:	LIGHT-WEIGHT SEMI-RIGID SLAB	
Name:	RockTech S 200 (for use up to 350°C)	Page 2 of 4

**Corrosion Resistance:
Chemical Neutrality:** Roxul Stonewool RockTech S 200 base mineral wool is chemically neutral and will neither cause nor promote corrosion.

**Corrosion Resistance:
Water Leachable Chlorides:** Roxul Stonewool RockTech S 200 mineral wool has a very low content of water leachable chloride, less than 6 ppm so it can be safely used on austenitic stainless steel. Meets the requirements for use over stainless steel in accordance with ASTM C795.

Fire: Roxul Stonewool RockTech S 200 slab is non combustible when tested according to international standards eg. ASTM E-136-82, DIN 4102, BS476 Pt4-1970, ISO R 1182.

Moisture Resistance Water: Roxul Stonewool RockTech S 200 is highly water repellent, non hygroscopic and non capillary. The water repellency is in accordance with BS 2972 (total immersion) is >96% (vol.). RockTech S 200 is water repellent in accordance with AGI Q 136.

Moisture Resistance Vapour Diffusion: Water vapour diffusion resistance factor of $\mu = 1.3$. This low value means that water can pass through and cool without condensing.

**Moisture Resistance:
Absorption from the air:** Roxul Stonewool absorbs very little water from the air. Tests show at relative humidity of 90% for 30 days the hygroscopic water content is around .004 volume per cent. The water vapour absorption (vapor sorption) in accordance with ASTM C110 4/C 1104 m is $\pm 0.02\%$ (vol).

Moisture Resistance Capillarity: Roxul Stonewool fibres and fibre coating repels water and prevents capillarity.

Melting Point: Melting point of Roxul Stonewool fibre is over 1000°C (1800°F)

	PRODUCT DATA SHEET	REVISION: 3
		DATE OF ISSUE: Nov 02
		CHKD: BH APPV: IRS

Product:	Roxul[®] Stonewool	P.D.S 12
Type:	LIGHT-WEIGHT SEMI-RIGID SLAB	
Name:	RockTech S 200 (for use up to 350^oC)	Page 3 of 4

Specific Heat: Roxul Stonewool specific heat factor is 0.84 kJ/kg per degree centigrade.

Calorific Value: Roxul Stonewool RockTech S 200 has a low organic matter content giving a low caloric value of around 600 kJ/kg.

Biological Properties: Roxul Stonewool RockTech S 200 material contains no nutrients and therefore provides no basis for growth of fungi, moulds or bacteria, nor does it attract insects, rodents or vermin.

Acoustic Properties: Roxul Stonewool RockTech S 200 mineral wool base material when measured according to ISO 354 and applied directly to the wall surface at a thickness of 50 mm gives the following:

H_z	125	250	500	1000	2000	4000
Coeff α S	0.23	0.74	1.14	1.11	1.05	1.05

Durability: Roxul Stonewool mineral wool has been proven in services for over 50 years in all types of exposure and as such will give effective protection for the lifetime of the equipment they insulate.

Compatibility: Roxul Stonewool mineral wool is compatible with all materials which it is likely to come into contact in normal industrial and building applications.

Environment: Roxul Stonewool mineral wool presents a very effective ecological profile in all elements of manufacture, recycling use, service life and energy efficiency of material. No CFC's or HCFC's are used in its manufacture.

	PRODUCT DATA SHEET	REVISION: 3
		DATE OF ISSUE: Nov 02
		CHKD: BH APPV: IRS

Product:	Roxul[®] Stonewool	P.D.S 12
Type:	LIGHT-WEIGHT SEMI-RIGID SLAB	
Name:	RockTech S 200 (for use up to 350°C)	Page 4 of 4

Health & Safety

RockTech S is NOT CLASSIFIED as HAZARDOUS according to NOHSC criteria as a consequence of the following events and conclusions about the health effects of long term occupation exposure to mineral wool insulation products.

- Over 50 years of extensive health research on Rockwool products in Europe has resulted in the scientific conclusion that there are no long term health problems from using Rockwool.
- In March 1995 the UK Health and Safety Executive concluded that Rockwool should not be classified as a potential carcinogen.
- Under note Q of the National Occupational health and Safety Commission (NOHSC) publication "List of Designated Hazardous Substances" (NOHSC; 1005-1999) the classification of NON-CARCINOGENIC is to apply.
- Under the European Union Criteria set out in 67/548/EEC a classification of CARC, Cat O applies, ie; "Not classifiable for carcinogenicity."
- Under World Health Organisation (WHO) and its Monographs Programme of the International Agency for Research on Cancer (IARC) it has been concluded that, "Rock (stone) wool are now considered not classifiable as to carcinogenicity to humans (Group 3),

It is recommended that for the handling and installation of Roxul Rockwool the internationally recognized Material Safety Data Sheet be followed;

PRODUCT DATA SHEET	REVISION: 3
	DATE OF ISSUE: Nov 02
	CHKD: BH APPV: IRS